

**Amendments to the Claims**

This listing of claims will replace all prior listings of claims in the application.

**Listing of Claims**

1.-11. (Canceled)

12. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 15, wherein said body is made from at least two compounded rubbers.

13. (Canceled)

14. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 15, wherein the NBR polymer has an NBR polar group in which the content of acrylonitrile is not greater than 30%.

15. (Currently Amended) An extrusion molded foamed cosmetic sponge puff having an intermediate cell structure in which closed cells partially communicate with each other, a water absorption of 5-500% and comprising a body ~~comprising~~ formed from a compounded rubber of an NBR polymer, an organic peroxide, a blowing agent and 1-100 parts by weight of a synthetic silicic acid, based on 100 parts by weight of the NBR polymer.

16. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 15, wherein said cells have a diameter of 200  $\mu$ m at a central portion thereof and a cell diameter of 700  $\mu$ m at an outer periphery thereof and the body further comprises from 10-200 parts by weight of a precipitated calcium carbonate.

17. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 15, wherein the synthetic silicic acid is present in an amount of at least 5 parts by weight.

18. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 16, wherein the synthetic silicic acid is present in an amount of at least 5 parts by weight.

19. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 15, wherein said cells have a diameter of 300  $\mu\text{m}$  at a central portion thereof and a cell diameter of 500  $\mu\text{m}$  at an outer periphery thereof.

20. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 12, wherein said cells have a diameter of 300  $\mu\text{m}$  at a central portion thereof and a cell diameter of 500  $\mu\text{m}$  at an outer periphery thereof.

21. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 14, wherein said cells have a diameter of 300  $\mu\text{m}$  at a central portion thereof and a cell diameter of 500  $\mu\text{m}$  at an outer periphery thereof.

22. (Previously Presented) The extrusion molded foamed cosmetic sponge puff of Claim 15, wherein the body does not contain an organopolysiloxane rubber.